

DUR-A-FLEX® Inc.**EPOXIES • MMA • URETHANES
COLORED QUARTZ AGGREGATES**95 Goodwin Street
East Hartford, CT 06108Tel: 800-253-3539 • Fax: 860-528-2802 • Internet: <http://www.dur-a-flex.com> • E-Mail: info@dur-a-flex.com

POLY-CRETE MDC

IMPORTANT! Read these instructions carefully several days prior to starting your work. Seek answers to any questions you may have before you begin. DUR-A-FLEX, Inc. maintains a Technical Staff that will be glad to answer your questions and give you advice pertaining to your particular installation. Large areas will require two or more mixers.

POLY-CRETE MDC is a 100% solids aromatic cementitious urethane system with a decorative chip broadcast. The system is installed at 1/4". This should be determined by service and cleaning temperatures, severity of traffic, point impact and loadings. POLYCRETE MDC uses 1/4 or 1/8 vinyl chips and clear seal coats to yield a decorative textured surface.

SURFACE PREPARATION

Surface should be profiled, clean, dry, oil free and sound. Shot Blasting or grit blasting are the preferred preparation methods. Please refer to the master "Surface Preparation Guide" for more information.

It is important that the perimeter edges of the floor area adjoining the walls, drains adjacent to any doorways, machinery pedestals and either side of day work joints, be keyed to produce a cross section 1/4" deep by 3/16" wide and running 6 inches away from, and parallel to the wall. Never feather edge POLY-CRETE MDC, always terminate in keyway groove at doorways and exposed edges. Refer to architectural drawings for details.

Do not apply at temperatures below 40°F or above 95°F.

MIXING AREA

Select a convenient mix area as close as possible to the application area and protect the surface from spillage by covering with a layer of cardboard and/or a sheet of plastic. Be generous with the amount of space allocated for this function. Do not mix this product in direct sunlight or when temperatures exceed 90°F. Exposure to high temperatures will greatly reduce the working time of this product.

DO NOT MIX UNTIL READY FOR IMMEDIATE USE.

PRIMING

No priming or sealing of the substrate is required. On oily concrete slabs, HI-SPEED Detergent/Degreaser is recommended. Very porous substrates may be pre-primed with POLY-CRETE TF (allow to cure a minimum of 6 hours @70°F) to prevent resins from being prematurely absorbed.

APPLICATION METHOD

POLY-CRETE MDC is applied by "Pin Rake" or "trowel method". POLY-CRETE MDC is typically applied at a thickness ranging from 1/8 to 3/16, yielding 3/16 to 1/4 inches including broadcast and seal coats. Proper planning is necessary for the satisfactory appearance of the finished floor. Install in sections to allow full width to be finished in 12 minutes (@70°F) or less to assure absence of placement lines. Prepare the surface as outlined in the DUR-A-FLEX "Surface Preparation Guide".

POLY-CRETE MDC is supplied in pre-measured units consisting of one pail of resin, one container of hardener and one bag of aggregate (powder). Pour resin into power mixer pail; scrape bottom and sides to assure all pigment is transferred. The resin and hardener should be added to a forced circulation pail mixer and pre-blended for approximately 30 seconds.

A Jiffler or Bird Cage mixer is **not recommended** for this product, however a low speed <500rpm high torque power drill and spiral mixing blade may be used. Gradually add aggregate until a homogenous mix is attained. (Approximately 1 minute) Move the paddle back and forth and scrape the bottom and sides of the pail while mixing. A properly mixed batch applies easier and has a uniform surface appearance. Incomplete mixing will cause an inconsistent finish or possible blistering. Have two mixing buckets that are rotated to assure minimum time between mixes. Clean mixing paddle and pail regularly to avoid mixing fresh material with older batches. Apply material immediately after mixing.

- A. Pour the entire batch onto the floor and spread with a 24" pin rake set at 1/4".
- B. Check pin rake every 1000 sq feet for pin wear. Adjust or have new rake ready to avoid interruption in the process.
- C. Trowel edges, drains and around equipment supports

"Warranties: Seller warrants that its goods, as described on the face hereof, are free from any defects in material or workmanship. Seller makes no other warranty, express or implied, and all implied warranties of merchantability and fitness for a particular purpose are hereby disclaimed. Seller shall not be liable for prospective profits or special indirect or consequential damages. Seller's sole liability and buyer's exclusive remedy for breach of any warranty as expressly limited, at seller's option, to replacement at the original F.O.B. point or refund of purchase price. Seller shall not be responsible for any claim resulting from failure to utilize product in the manner in which it was intended and in accordance with instruction provided for use of product. Any claim for breach of warranty shall be deemed waived unless buyer shall give seller written notice of such claim within sixty (60) days after delivery and shall allow seller reasonable opportunity to investigate claim and inspect product."

- D. Immediately roll with a spiked roller with 15/16" pins to eliminate lines and help release air.
 - E. Spike Rolling must be completed immediately after leveling of material to eliminate any residual roller marks in the finished surface (Within 12 minutes of mixing @ 70° F).
 - F. The vinyl chips must be broadcast UP into the air, dispersing evenly and vertically at an approximate rate of .0.6lbs per sq ft into the wet surface and 2 mixes behind the wet edge, ensuring that the surface is completely covered. Broadcasting should be completed within 15 minutes of mixing each relevant batch.
 - G. Do not spike roller areas that have been broadcast
- The time window at which MDC is broadcast is extremely critical:**
- Too early and the surface may become uneven
 - Too late and the chips may not penetrate into the matrix surface.
- H. Allow to cure for a minimum of 10hrs (@70°F). Remove excess aggregate by brush.
 - I. Scrape or lightly sand surface and remove all deposits by use of vacuum cleaning equipment

CURE

Allow a minimum of 8 hours cure before light foot traffic at 75 ° F, and a minimum of 24 hours is required at 50°F. Additional time must be allowed for heavier loads or lower temperatures. Contact the DUR-A-FLEX Technical Department for more information.

MOISTURE CONCERNS

Please refer to the [Floor Evaluation Flow Chart](#) in the Contractor's Center of our website for a step-by-step process to determine the condition of the concrete. Typical Moisture levels should be no greater than 92%RH and no more than an orange rating on the Nautilus Floor Evaluation Chart.

TOPCOAT INSTRUCTIONS

Appearance, aggregate size, texture and the type of traffic or chemical abuse the floor receives will determine what type of topcoat should be applied. Consult DUR-A-FLEX Inc. for technical assistance to determine whether DUR-A-GLAZE #5 or DUR-A-GLAZE NOVOLAC is to be used as the top coat.

(option 1 DUR-A-GLAZE NOVOLAC)

Use a Jiffler type mixer to combine 1 part DUR-A-GLAZE hardener with 2 parts DUR-A-GLAZE NOVOLAC. Mix thoroughly for 3 minutes. Mix only what can be used within 5 - 10 minutes. Apply combined epoxy with a 12" flat squeegee. Pour a 4"- 6" ribbon of blended epoxy on the floor. Spread the epoxy by moving the squeegee in a continuous semi-circular movement from left to right while moving backward slowly and pulling the epoxy with you. Move squeegee slowly and apply sufficient pressure to obtain a uniform appearance. Avoid leaving puddles and squeegee marks. Walk on the surface with spiked golf shoes and back-roll the area with a 3/8" non-shed roller.

(option 2 DUR-A-GLAZE #5)

DUR-A-GLAZE #5 SQUEEGEE & ROLL METHOD

- A. Prepare the surface as outlined in the DUR-A-FLEX **Surface Preparation Guide**.
- B. Add hardener to resin container. Mix thoroughly with a Jiffler type mixer on a slow speed (450 rpm) 1/2" electric drill for 1 minute. Always scrape the sides and bottom of resin container to assure thorough blending. Keep hardener and resin containers covered to prevent moisture from entering. THOROUGH BLENDING IS MANDATORY. Use blended material without delay. Pot life and working time is shorter at higher temperatures.
- C. Topcoat for cove and floor should be done at the same time to avoid roller or squeegee marks.
- D. Pour entire batch in a long "ribbon", 4 to 6 inches wide, along a wall or a joint at your starting point. Watch your spread rate! The blended hardener and resin can be spread with a flat or fine serrated squeegee and then immediately back-rolled with a short nap, Non-Shed paint roller (*mohair type rollers typically work best*). Do not re-roll material after 3 minutes. Complete all procedures within a 10 minute working time window.
- E. Remove all masking tape as you proceed before it gets out of reach.
- F. Allow first coat to cure until dry, 4-6 hours depending on temperature of floor and surrounding air. On grade or below grade concrete floors are usually considerably cooler

than surrounding air, so drying time may be extended.

Apply optional second coat to obtain a more uniform appearance and more durability. Apply with a short nap, non-shed roller at appropriate spread rate and preferably at a 90-degree angle to first coat application. Follow mixing instructions outlined in previous section and apply succeeding coats as soon as possible after previous coat dries. (within 24 hours) **NOTE: This product is best suited for application in temperatures between 55°F and 85°F. Full chemical and abrasion resistance occurs in 7 days at 77° F.** At lower temperatures these

properties will be attained more slowly. Protect floor from chemical exposure and abrasive wear during this time.

CAUTION

Refer to Material Safety Data Sheet for proper personal protective equipment to use when handling this product. Use only as directed. **KEEP OUT OF REACH OF CHILDREN.** Do not reseal moisture-contaminated hardener. This will result in carbon dioxide generation on possible violent rupture of containers.

Before using any DUR-A-FLEX, Inc. product, be sure the Material Safety Data Sheet is read and understood.