

# Dur-A-Crete Epoxy Grout Mixing Guide

This guide indicates the proper amount of Crete Sand with the proper amount and size of Pea Gravel used for Dur-A-Crete Epoxy Grout. The same amount of resin and hardener is used for all application thicknesses.

**Mix ratio per batch is:** 24 ounces of Dur-A-Glaze #4 hardener and 48 ounces of Dur-A-Glaze #4 resin or Shop Floor resin.

*\*Use only Dur-A-Crete sand. Pea gravel must be washed and dried.*

Application Thickness (inches)	Crete Sand	Dur-A-Flex Pea Gravel Size (inches)	Additional Pea Gravel (Gallons)	Square Feet Per Batch	Cubic Feet Per Batch
1/4	(1) 40 lb bag	-	-	20	0.41
1/2	(1) 40 lb bag	1/8	1 gallon	12	0.51
3/4	(1) 40 lb bag	1/8	1 gallon	8	0.51
1	2 gals	1/8 + 3/8	1 gal - 1/8 1 gal - 3/8	6	0.51
1 1/2	2 gals	1/8 + 3/8	1 gal - 1/8 1 gal - 3/8	4	0.51
2	2 gals	1/8 + 3/8	1 gal - 1/8 1 gal - 3/8	3	0.51
3+	2 gals	1/8 + 3/8	1 gal - 1/8 1 gal - 3/8	2	0.51

## Material Weight Per Gallon

Material	Pounds per gallon
Pea Gravel (1/8 & 3/8)	12
Crete Sand	13.5

\*Pea Gravel is available from Dur-A-Flex, in 50 lb. bags